

ASTM A106	Tensile strength, min, psi (MPa)	Yield strength, min, psi (Mpa)	Elongation in 2" (50mm), min (%): Longitudinal	Elongation in 2" (50mm), min (%): Traverse
Grade B	60,000 (415)	35,000 (240)	30	16.5
Grade C	70,000 (485)	40,000 (275)	30	16.5